

Product Information

Aflow extrusion plastometer

CTA: 168420 169603



Aflow extrusion plastometer

Applications

Speed, operator-independence and high test-result reproducibility and repeatability – all these things matter in research and development and in 24-hour operation, as in production control.

A defining feature of Aflow is its high level of automation - easy cleaning and defined pre-compacting at the touch of a button, stepless test-load settings - Aflow adapts to your testing requirements.

Aflow can be operated in stand-alone mode via a modern touch display or on a PC with ZwickRoell testing software.

The basic version of the Aflow extrusion plastometer is designed to perform MFR and MVR tests in accordance with Methods A, B, C and D. This can be done using an automatic extrudate cutter and balance. Tests can be performed in accordance with the following standards:

- ISO 1133, ASTM D1238, ASTM D3364, JIS K 7210.

Advantages and features

Fast, effortless cleaning and pre-compacting

Aflow's pneumatic cleaning device enables cleaning and pre-compacting to be performed at a preset pressure. The Clean and Pre-compact option allows variable adjustment of the cleaning and pre-compacting pressure, while a switch on the cleaning unit allows one of the two pressure steps to be selected.



Optimum test sequence - time-saving and operator-friendly

The pneumatic pre-compaction feature allows the polymer to be defined and evenly pre-compacted at the press of a button—saving time and effort. To further accelerate the test procedure after the test, it is possible to eject the remaining material from the extrusion barrel with a force of up to 80 kg and then clean it with a pneumatic cleaning device at the press of a button.

Flexibility via stepless test load up to 50 kg

Test loads in Aflow can be adjusted steplessly from 0.325 kg to 50 kg. A multi-stage test can be performed effortlessly to Method D purely by means of presets in the software. This allows several tests with different weight stages to be carried out with a single barrel filling.

Flexible - use with or without PC

The new standardized operating philosophy allows the operator to move easily between instrument and PC and always feel at home.

Intuitive, workflow-based touch operation

All test-related settings are grouped logically and are separated from higher-level system settings. The operator is guided through test configuration step by step. The saved test configuration can easily be exported and transferred to other instruments.

PI 780 0319

Product Information

Aflow extrusion plastometer

Rapid familiarization with user management, including stand-alone mode

Integrated user management allows the operator's input options to be reduced to a minimum. Users see only what is important to them, allowing them to focus on the task at hand right from the start.

Live MVR

The MVR is shown "live" in graphic form in stand-alone mode and in the ZwickRoell testing software. This allows both melting process and behavior to be followed precisely during measurement.

Managing multiple extrusion plastometers via one PC

With multi-instrument operation up to 6 extrusion plastometers can be controlled from one PC. Central operation and results saving from a single work station makes for efficiency and provides a quick overview of all tests currently in progress. For multi-instrument operation the required Ethernet interfaces must be available on the PC; otherwise Ethernet hubs must be used.

Product Information

Aflow extrusion plastometer

Technical data

Basic instruments

Please note:

requires dry, oiled air

Type Item No.	Aflow extrusion plastometer (230 V) 1043954	Aflow extrusion plastometer (110 V) 1043955	
Test load	0.325 ... 50 (step by step or stepless)	0.325 ... 50 (step by step or stepless)	kg
Compressed air, oiled, dry	5 ... 10	5 ... 10	bar
Dimensions:			
Height	1021	1021	mm
Width	580	580	mm
Depth	596	596	mm
Weight, approx.	114	114	kg
Test temperature	+50 ... +450	+50 ... +450	°C
Display	Capacitive touch display	Capacitive touch display	
Resolution of the temperature display	< 0.001	<0.001	K
Number of savable parameter sets	> 100	> 100	
Interfaces	<ul style="list-style-type: none"> • Ethernet port to connect a PC • 2 x USB port to connect a printer or USB stick • RS-232 port for raw data export, data output: serial number, specimen number, number of extrudates, density (user specifications) density at test temperature, overall weight of the extrudates, MFR average value, MVR average value, MFR and MVR individual values • RS-232 port for connecting the analytical scale (from the ZwickRoell product range) 		
Temperature accuracy in the range of 0 ... 75 mm above the die, in the temperature range of 50 °C ... 450 °C	< 0.3 ¹⁾	< 0.3 ¹⁾	K
Time measurement:			
Error limit (Method A)	±0.02 (with automated extrudate cutter)	±0.02 (with automated extrudate cutter)	s
Error limit (Method B)	±0.01	±0.01	s
Travel measurement:			
Error limit (Method B)	±0.02 mm (ISO 1133) / ±0.4% of 6.25 mm (ASTM D1238)	±0.02 mm (ISO 1133) / ±0.4% of 6.25 mm (ASTM D1238)	
Resolution	< 0.0005	< 0.0005	mm
Piston speed, max.	2000 ²⁾	2000 ²⁾	mm/min
Multi-instrument operation on one PC:			
Available main memory, min.	1.54	1.54	GB
Clock frequency	3	3	GHz
Connectible Aflow extrusion plastometer per PC	6	6	

Product Information

Aflow extrusion plastometer

Type Item No.	Aflow extrusion plastometer (230 V) 1043954	Aflow extrusion plastometer (110 V) 1043955
Included in the scope of delivery:	<ul style="list-style-type: none"> Ethernet cable Cleaning accessories (cleaning piston, cleaning brush, cleaning pads (500 pieces)) for barrel Test granulate and filling chute for granulate 	
Power input specifications		
Power supply	220 to 240 V, 1L/PE/N	100 to 127 V, 1L/PE/N
Power consumption (full load), approx.	0.6	0.6 kVA
Power frequency	50/60	50/60 Hz

1) Spatial and temporal, to ISO 1133-2

2) To ensure proper force control, the piston speed cannot exceed 75% of this value

Accessories required

Extrusion barrel (1 x required)

An extrusion barrel must be chosen to suit the materials to be tested. Different plastics containing fluoride, such as PTFE and PFA, release hydrofluoric acid, which corrodes the material of the extrusion barrel. For these types of plastics, extrusion barrels made from a special type of steel alloy are used.

Test material	Inner diameter [mm]	Hole	Properties	Item No.
Plastic, fluorine free	9.55	Finely honed	Wear resistant	050888
Plastic, containing fluorine / fluorine free	9.55	Finely honed	Acid-resistant, wear-resistant	1069372

Piston (1 x required)

At least one piston must be selected, in accordance with the materials to be tested. Various plastics (e.g. PTFE and PFA) which contain fluorine release hydrofluoric acid, which attacks the extrusion barrel material. For these plastics pistons made of a special steel alloy are used. These pistons have only limited suitability for filled plastics. For these the wear-resistant version is recommended. For tests to ISO 1133-1997, a piston with non-rounded edges (sharp-edged) is required.

Test material	Standard	Properties	Item no.
Plastic, fluorine free	ISO 1133	Wear resistant	032298
Plastic, containing fluorine	ISO 1133	Resistant to acid	032299
Plastic, fluorine free	ISO 1133-1997	sharp-edged, wear resistant	032300
Plastic, fluorine free	ASTM D1238	Wear resistant	1015333

Dies (scope of supply 2 pieces, 1 x required)

At least one die pair must be selected. It should suit the materials to be tested. Scope of delivery: 2 pieces + cleaning rod.

Item No.	312342	325554	001351	092326
Material	Sintered material	Sintered material	Sintered material	Sintered material

Product Information

Aflow extrusion plastometer

Item No.	312342	325554	001351	092326
Test material	Plastic, containing fluorine, without fluorine	Plastic, containing fluorine, without fluorine	Plastic, containing fluorine, without fluorine	PVC
Standard	ISO 1133 and ASTM D1238	ISO 1133 and ASTM D1238 Method C	BS 2782-7, Method 720A-1997	ASTM D3364
Dimensions:				
Length	8	4	8	25.4 mm
Inner diameter	2.095	1.05	1.18	2.095 mm
Properties	Wear resistant, resistant to acid	Wear resistant, resistant to acid	Wear resistant, resistant to acid	Wear resistant, resistant to acid

Optional accessories

Extrudate cutters

Description	Item number
<p>Extrudate cutter</p> <p>The automatic extrudate cutter is used to achieve precise extrudate cutting. The die plug prevents premature outflow of the material when plastics with high flow-rates ($> 10 \text{ cm}^3/10 \text{ min}$ at load 0.375 kg) are being tested.</p> <p>Extrudate cutter, automatic activation, automatic control via time interval or manually via push-button, includes replacement blades (4 pieces)</p>	032301

Die plug

When the die plug is in use, an extrudate cutter is required in order to eject the die plug automatically when the test begins.

Description	Item number
Die plug for testing plastics with high flow-rate; ceramic plug included ¹⁾	032302

¹⁾ Required: 1x extrudate cutter

Separating pane

Description	Item number
Separating pane for automatic extrudate cutter, for collecting individual extrudates	032303

Cleaning

Dimensions of pneumatic cleaning device unit including basic instrument: 1200 x 580 x 596 mm (H x W x D)

Description	Item number
Pneumatic cleaning device	032304
Option cleaning/pre-compaction: Software-controlled, variable switching option for pressure setting for pre-compaction and cleaning ¹⁾	032306

¹⁾ Required for this: Pneumatic cleaning device